



13th June 2011

Watson Wood Fuel
Foxholes
Driffield

Test for hardwood Briquettes Date Analysed : 23rd May to 6th June 2011

Report Date : 13th June 2011

Customer Reference : WF002BR

Test Method	Sample Reference	Briquette
SP20	Total Moisture %	6.5
CA 2	Analysis Moisture %	4.0
CA 3	Ash %	0.9
**	Fixed Carbon %	16.0
CA 31	Sulphur %	0.01
CA 11	Gross Calorific Value kJ/kg	18476
**	Net Calorific Value kJ/kg	17156
CA 9	Carbon %	45.62
CA 9	Hydrogen %	5.31
CA 9	Nitrogen %	2.64
Test results calculated to "As received" Moisture Basis		

